



# Accura<sup>®</sup> ABS Black (SL 7820)

ABS Class

Simulate and replace CNC-machined black ABS articles

## Post-Cured Material

MEASUREMENT	CONDITION	METRIC	U.S.
Tensile Strength (MPa/PSI)	ASTM D 638	45-47	6525-6815
Tensile Modulus (MPa/KSI)	ASTM D 638	1890-2440	274-354
Elongation at Break (%)	ASTM D 638	6-13	6-13
Flexural Strength (MPa/PSI)	ASTM D 790	75-78	10875-11310
Flexural Modulus (MPa/KSI)	ASTM D 790	2260-2370	328-344
Impact Strength (J/m /Ft-lbs/in)	ASTM D 256	39-56	0.73-1.05
Heat Deflection Temperature	ASTM D 648 @ 66 PSI	51 °C	124 °F
Coefficient of Thermal Expansion (µm/m-°C / µm/in-°F)	ASTM E 831-93 25-50 °C	93	52
Glass Transition (Tg)	DMA, E''	62 °C	144 °F
Hardness, Shore D		86	86

## Features

- Rigid and tough
- Functional assemblies
- Short-run production parts

## Liquid Material

MEASUREMENT	CONDITION	VALUE
Viscosity	@ 30 °C (86 °F)	210 cps
Penetration Depth (Dp)		4.5 mils
Critical Exposure (Ec)		10 mJ/cm <sup>2</sup>
Color		Black
Solid Density	@ 25 °C (77 °F)	1.16 g/cm <sup>3</sup> at 25 °C
Liquid Density	@ 25 °C (82 °F)	1.13 g/cm <sup>3</sup> at 25 °C

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, or with end use. 3D Systems makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

© 2017 by 3D Systems, Inc. All rights reserved. Specifications subject to change without notice. The 3D logo and Accura are registered trademarks of 3D Systems, Inc.



**middle east**  
3D PRINTING THE FUTURE

**3D SYSTEMS<sup>®</sup>**  
DISTRIBUTOR | Middle East & North Africa

U.A.E Office : 3204, Prism Tower, Business Bay, P.O. Box 28820, Dubai, U.A.E.

K.S.A Office : Al Saif Tower, 6th Floor, King Abdullah Street, Near Intersection with Olaya Street, Riyadh, K.S.A.

Tel : +971.4.443.3853 ; Fax : +971.4.443.3938 ; Email : info@3d-me.com ; Website: www.3d-me.com