



Accura[®] HPC High Performance Composite

A high-speed, high-rigidity engineered nanocomposite

Post-Cured Material

MEASUREMENT	CONDITION	METRIC	U.S.
Tensile Strength (MPa PSI)	ASTM D638	66-89	9570-12910
Tensile Modulus (MPa KSI)	ASTM D638	9000-9700	1305-1407
Elongation at Break	ASTM D638	0.8-1.9 %	0.8-1.9 %
Flexural Strength (MPa PSI)	ASTM D790	137-157	19870-22770
Flexural Modulus (MPa KSI)	ASTM D790	8700-10200	1262-1479
Izod impact notched (J/m ft-lbs/in)	ASTM D256	14-17	0.3
Heat Deflection Temperature	ASTM D 648 @ 66 PSI @ 264 PSI	73 °C 62 °C	163 °F 144 °F
Poissons Ratio	ASTM D638	-0.32	-0.32
Coefficient of Thermal Expansion, 50-100 °C (ppm/°K ppm/°F)	ASTM E 831-93	64.2	35.7
Coefficient of Thermal Expansion, 100-150 °C (ppm/°K ppm/°F)	ASTM E 831-93	81.7	45.4
Dielectric Constant at 1MHz	ASTM D150	4.2	4.2
Solid Density (g/cm ³ lbs/in ³)		1.61	0.058
Shore D		80	

Liquid Material

MEASUREMENT	CONDITION	
Viscosity	@ 30 °C (86 °F)	700-1000 cps
Penetration Depth (Dp)		5.0 mils
Critical Exposure (Ec)		5.9 mJ/cm ²
Color		White
Liquid Density		1.60 g/cm ³

Features

- Produces extremely strong and rigid parts
- High-production speeds
- Smooth easy-to-finish surfaces
- High temperature resistance
- Lowest viscosity

Applications

- Automotive and aerospace wind tunnel models
- Abrasion-resistant structures
- Jigs, fixtures and tooling applications
- Electrically insulating enclosures



U.A.E Office : 3204, Prism Tower, Business Bay, P.O. Box 28820, Dubai, U.A.E.
K.S.A Office : Al Saif Tower, 6th Floor, King Abdullah Street, Near Intersection with Olaya Street, Riyadh, K.S.A.
Tel : +971.4.443.3853 ; Fax : +971.4.443.3938 ; Email : info@3d-me.com ; Website: www.3d-me.com



DISTRIBUTOR | Middle East & North Africa